



HEMPEL'S LIGHT PRIMER 45551

45551: BASE 45559: CURING AGENT 95360

Description: HEMPEL'S LIGHT PRIMER 45551 is a two-component polyamide adduct cured epoxy high build paint. It forms a hard and tough coating resistant to water and petroleum products.

Recommended use: As a primer under and above the water line on boats made of aluminium, glass fibre reinforced polyester, plywood and steel. Also for prevention and repair of osmotic blistering in the glass fibre reinforced polyester, and for protection of keels and rudders.

Availability: Subject to special agreement.

PHYSICAL CONSTANTS:

Shade nos/Colours: 11630*/ Off-white.
Finish: Flat
Volume solids, %: 52 ± 1
Theoretical spreading rate: 5.2 m²/l [208.5 sq.ft./US gallon] - 100 micron/4 mils
Flash point: 24 °C [75.2 °F]
Specific gravity: 1.3 kg/litre [10.9 lbs/US gallon]
Dry to touch: 3 - 4 hour(s) 20°C/68°F
Fully cured: 7 day(s) 20°C/68°F
VOC content: 439 g/l [3.6 lbs/US gallon]
**other shades according to assortment list.*

The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.

APPLICATION DETAILS:

Version, mixed product: 45551
Mixing ratio: BASE 45559: CURING AGENT 95360
2:1 by volume
Application method: Air spray (HVLP) / Conventional (Gravity feed) / Conventional (Suction feed) / Conventional (Pressure feed)
Fluid tip: 1.6-1.8 mm/ 1.4-1.8 mm/ 1.4-1.8 mm/ 1.4-1.8 mm
Air pressure: 0.7 bar at nozzle/ 5 bar/ 5 bar/ 5 bar

Thinner (max.vol.): Airless spray / Brush
08450 (5%) / 08450 (5%)
(Spray data is indicative and subject to adjustment)
Pot life (Airless spray): 2 hour(s) 20°C/68°F
Pot life (Brush): 6 hour(s) 20°C/68°F
Nozzle orifice: 0.019 - 0.023 "
Nozzle pressure: 175 bar [2537.5 psi]
(Airless spray data are indicative and subject to adjustment)

Indicated film thickness, dry: 100 micron [4 mils]
Indicated film thickness, wet: 200 micron [8 mils]
Recoat interval, min: According to specification.
Recoat interval, max: According to specification.

Safety: Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.

SURFACE PREPARATION: See separate APPLICATION INSTRUCTIONS

APPLICATION CONDITIONS: See separate APPLICATION INSTRUCTIONS

PRECEDING COAT: See separate APPLICATION INSTRUCTIONS

SUBSEQUENT COAT: See separate APPLICATION INSTRUCTIONS

REMARKS:

Note: HEMPEL'S LIGHT PRIMER 45551 4555111630

The information given in the Product Data Sheet is intended for commercial use.

ISSUED BY: HEMPEL A/S

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.