



HEMPPEL'S TEAK COLOUR RESTORER 67462

Description:	HEMPPEL'S TEAK COLOUR RESTORER 67462 is a pigmented wood oil containing antimould agents to prevent discolouration. The wood obtains a golden colour after application.
Recommended use:	On new as well as on wood previously treated with oils or wood preservatives including teak. Not for deck areas.
Availability:	Part of European Yacht assortment. Local availability subject to confirmation.
PHYSICAL CONSTANTS:	
Shade nos/Colours:	65220/ Teak
Finish:	Transparent, Brown.
Volume solids, %:	38 ± 1
Theoretical spreading rate:	see REMARKS overleaf
Flash point:	62 °C [143.6 °F]
Specific gravity:	0.9 kg/litre [7.3 lbs/US gallon]
Surface dry:	1 approx. hour(s) 20°C/68°F 2 (approx.) hrs at 10°C/50°F
Dry to touch:	6 - 8 hour(s) 20°C/68°F 12-16 hours at 10°C/50°F
VOC content:	538 g/l [4.5 lbs/US gallon]

The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.

APPLICATION DETAILS:

Application method:	Brush / Dipping
Thinner (max.vol.):	Do not dilute.
Cleaning of tools:	HEMPPEL'S THINNER 08231 or HEMPEL'S THINNER 08111
Indicated film thickness, dry:	15 micron [0.6 mils]
Indicated film thickness, wet:	50 micron [2 mils]
Recoat interval, min:	According to specification.
Recoat interval, max:	According to specification.
Safety:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.



HEMPPEL'S TEAK COLOUR RESTORER 67462

APPLICATION CONDITIONS:

New wood except teak and vacuum impregnated wood: Saturate the dry, clean surface with suitable wood preservative, allow to dry. Apply two coats of the product on internal areas and three coats on weather exposed areas.

New teak and vacuum impregnated wood: Apply two coats of the product. The surface must be completely clean and dry. Teak is preferably cleaned with:HEMPPEL'S TEAK CLEANING POWDER 67543.

Previously treated wood: Remove all contaminants with a suitable detergent. Remove all loose material, remove dust by vacuum cleaning Treat any bare spots with suitable wood preservative (not teak). Apply 1-2 coats of the product. The product should preferably be thinned 1:1 with suitable wood preservative to keep the shade.

SUBSEQUENT COAT:

None.

REMARKS:

Application(s)

The surface must be completely clean and dry. Do not apply under humid conditions or at temperatures below: 5°C/41°F.

The moisture content in the wood should not exceed: 16%. In confined spaces provide adequate ventilation during application and drying.

The practical spreading rate is:10-20m²/l/408-846sq.ft/US gallons for smooth surfaces. On rough or absorbing surfaces the spreading rate will be lower, typically:5-10 m²/l/204-408 sq.ft./US gallons.

As autoignition of rags impregnated with the product is possible, they should be safely disposed of after use.

Avoid cleaning or grinding of the surface with steel wool or similar as this might cause rust stains.

HEMPPEL'S TEAK COLOUR RESTORER 67462

The information given in the Product Data Sheet is intended for commercial use.

Note:

ISSUED BY:

HEMPPEL A/S

6746265220

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.

HEMPPEL

Product Data Sheet