



HEMPEL'S TEAK OIL 67571

Description:	HEMPEL'S TEAK OIL 67571 is based on alkyd resin and drying oils with low viscosity. Good penetration ability and weather resistance. Contains antimould agents.
Recommended use:	As a wood treatment oil on new teak and teak previously treated with oil based products, interior and exterior. Not suited for varnished wood.
Availability:	Part of European Yacht assortment. Local availability subject to confirmation.
PHYSICAL CONSTANTS:	
Shade nos/Colours:	00000/ Transparent
Finish:	Transparent
Volume solids, %:	21 ± 1
Flash point:	62 °C [143.6 °F]
Specific gravity:	0.8 kg/litre [6.9 lbs/US gallon]
Dry to touch:	8 approx. hour(s) 20°C/68°F 18 (approx.) hrs at 10°C/50°F
VOC content:	621 g/l [5.2 lbs/US gallon] <i>The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.</i>
APPLICATION DETAILS:	
Application method:	Brush / Dipping
Thinner (max.vol.):	Do not dilute.
Cleaning of tools:	HEMPEL'S THINNER 08231 or HEMPEL'S THINNER 08111
Indicated film thickness, dry:	Not relevant. see REMARKS overleaf
Indicated film thickness, wet:	Not relevant. see REMARKS overleaf
Recoat interval, min:	According to specification.
Recoat interval, max:	According to specification.
Safety:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.



HEMPEL'S TEAK OIL 67571

SURFACE PREPARATION:

Untreated wood: Remove oil and grease with suitable detergent. Hose down with clean fresh water. Clean with HEMPEL'S TEAK CLEANING POWDER 67543. Rough surfaces may possibly be grinded with paper 180-220. Remove dust and loose material.

Previously treated wood: Remove oil and grease with suitable detergent. Hose down with clean fresh water. Allow the surface to dry

APPLICATION CONDITIONS:

The surface must be completely clean and dry. Application should only take place in dry weather with temperatures above: 5°C/41°F

In confined spaces provide adequate ventilation during application and drying.

SUBSEQUENT COAT:

None.

REMARKS:

Application(s)

Apply the product abundantly. Allow the wood to absorb the sealer for some minutes before any surplus is removed with clean rags to avoid a glossy film after drying. It is possible to grind the still wet sealer with paper 180-220, grind parallel to veins.

Spreading rate depends on texture and absorptivity of substrate.

Maintenance is carried out by HEMPEL'S TEAK OIL 67571, which is applied in a thin coat followed by removal of any surplus with clean rags.

Spillage, remains, discarded clothes and similar should be discarded in a fireproof container due to the risk of auto ignition.

Note:

HEMPEL'S TEAK OIL 67571

The information given in the Product Data Sheet is intended for commercial use.

ISSUED BY:

HEMPEL A/S

6757100000

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL'S GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.